

Sikaflex 1 CSL

High Performance, Self-leveling, One Component, Polyurethane Sealant

FEATURES

Tack-free	time		1-21	iours
	1,0,5795/3	1 . C. M. C. S.	74	If It'll be became

- ▲ Final cure......3-5 days
- ▲ Shore A Hardness.....45+/-5
- ▲ Joint Movement....+/-25%
- ▲ Tensile Strength.........550psi
- ▲ Elongation......700%

Sika's convenient packaging in either angle-seal sausage or 30 fl. oz. cartridge allows for easy application.

APPLICATIONS

- ▲ Sidewalks
- ▲ Balconies
- Pavements
- ▲ Terraces
- Warehouses
- Factories
- Civil Structures
- ▲ Plazas



- ▲ Unique "angle-sealed" sausage packaging; no gun required. 30 fl. oz. cartridge also available for easy gunnability.
- Rapid final cure and tack-free times, reducing the risk of pre-cure failures and dirt pick-up.
- No bubbles, no tooling required.
- Higher hardness for traffic durability, yet maintains joint movement capability.
- ▲ Meets ASTM C 920 and Federal Specification TT-S-00230C.





1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers

For the location of your nearest Sika sales office, contact your regional center.

Eastern Region 5 Summit Place Suite 201 Branford, CT 06405 Phone: 203-488-7790 Fax: 203-488-7790 Central Region 2190 Gladstone Court Suite A Glendale Heights, IL 60139 Phone: 630-924-7900

Fax: 630-924-8508

Western Region 12767 East Imperial Hwy. Santa Fe Springs, CA 90670 Phone: 562-941-0231 Fax: 562-941-4762 Sika Canada, Inc. 601 Delmar Avenue Point Claire, Quebec H9R4A9 Phone: 514-697-2610 Fax: 514-694-2792



